

Technical Data Sheet

• Product Description:

- Thermal grease is also called paste, is made from organic silicone and heat-conducting materials
- Never cured, and it can maintain the paste state in the -40 to 180 $^{\circ}\mathrm{C}$ range
- Excellent thermal conductivity, electrical insulation, weather and temperature resistance
- · Comply with EU ROHS directive requirements

• Product Application:

- It is widely used in various electronic products, and the contact surface between the heating element and the heat radiating device in the electrical equipment
- It is used in the contact surface between the radiator of the LED lamp and the PCB. Suitable for SMD high-power lamp
- CPU, power amplifier, thermistor, power module, etc.

• Product Instruction:

- Please make sure the surface is absolutely clean before use
- The thermal grease could be coated on the objects directly or by brush

• Caution:

- Please note that the thickness of the thermal grease will affect the efficiency of heat conduction, so please coat moderate quantity on the objects surface., and the thinner, the better
- Keep away from children
- If contact with the skin, wipe clean, and then rinse with water; if contact with eyes, immediately wash with water, and go to the hospital to check

• Technical Specification:

MT-1202 Thermal Grease

Performance	Data
Colour	White
Thermal conductivity (W/m-k)	1.0 ± 0.2
Density (g/ml)	1.9 ± 0.08
Cone penetration (1/10 mm)	360±10
Vdaf (200°C, 24h)	<1.0%
Breakdown voltage (Kv/mm)	>5.0
Operating temperature (°C)	-40~200
Limit temperature (°C)	-50~250

• Packing Specification:

- 1KG/ barrel, 12KG/ box
- · 300ml/ tube (500g/tube), 25 PCS / box
- · 25KG/barrel

Storage And Transport

- This product should be stored in a dry, cool place, avoid rain, sun exposure, storage period of twelve months (25° C). During storage, a small amount of silicone oil may precipitate, and this is a normal state, does not affect the use of results. If necessary, should be used after mixing evenly.
- Such products are non hazardous and can be transported in general chemicals



Contacts: Chris